

Arcrete G110

High-Range Water Reducing Concrete Admixture for Hot Weather Readymix Concrete Applications
ASTM C494 Type A, D & G and BS EN 934-2

Description

Arcrete G110 is a High-Range Water Reducer developed to enhance and improve the slump retaining properties of concrete, whilst providing improved ultimate compressive strengths. It can be used at a range of dosage levels to:

- ✓ Reduce water content
- ✓ Reduce Cement Content
- ✓ Increase compressive strength
- ✓ Increase workability

Arcrete G110 is highly flexible and effective over a wide range of cement contents and types. The product is especially beneficial in either high strength or high durability concrete mix designs in hot climatic conditions.

Typical Properties

Appearance: Dark Brown Liquid

Specific Gravity: 1.16 at 20°C

Air Entrainment: 1.0% Max from control Mix.

Chloride Content: Nil according to BS5075

Compatibility

With Cements:

Arcrete G110 is compatible with all Portland, Pozzolanic and blast furnace cements. It is also compatible with concrete containing fly ash and silica fume.

With Other Admixtures:

Arcrete G110 performance of the product will be affected by the presence of other chemical admixtures. We recommend Arkaz be contacted for Advice in these circumstances.

Addition Rates

Range:

0.4%-2 % (v/w) by wt. of cement

400 ml - 2000 ml per 100 kg cement

As with most products of this type the magnitude of the effect obtained with **Arcrete G110**, is governed by the quantity of product used, water-cement ratio, and the specific nature of the concrete and constituent materials.

It is necessary, therefore, to assess performance under site conditions using actual materials to determine optimum performance and dosage and effect on both plastic and hardened concrete properties such as cohesiveness, workability retention, setting characteristics, rate of early strength gains, ultimate strength and shrinkage where these are of importance.

Effects of Overdosing

Serious overdosing of **Arcrete G110** will generally produce a concrete mix of even greater workability, set retardation and a slight increase in air entrainment may be noticed. In SRC mixes and in cooler weather, set retardation will be further increased.

Dispensing

It is preferable that **Arcrete G110** should be introduced into the mixer by means of independent automatic dispensing equipment. Such equipment or advice on dispensing can be obtained from Arkaz.

Method of Use

Arcrete G110 is supplied ready for use. It should be added to concrete mixes either during the mixing cycle or at the same time as the water, or alternatively, it should be added in its supplied form to a normal concrete mix a few minutes before the pour is made.

In the latter case, further mixing should be provided to ensure complete dispersion.

Health and Safety

For further information, Check Product Material Safety Data Sheet or please consult Arkaz

Technical Service

The technical service department of Arkaz Alsharq Building Materials is available to assist in the correct and best use of our products. These resources and advice are at your disposal entirely without obligation. Please contact:

Arkaz Alsharq Building Materials
Dammam 2nd Industrial Area - Road 135
PO Box 2572, Khobar, 31952
Saudi Arabia.

Tel: 013 808 6970

Fax: 013 812 6541

info@arkaz.com

www.arkaz.com

The information given is based on data and knowledge considered to be true and accurate and is offered for the user's consideration, investigation and verification. Since the conditions of use are beyond our control we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale including those limiting warranties and remedies which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would violate or infringe statutory obligations or any rights belonging to a third party.

These products may be covered by patents or patents pending. Copyright 2017
Printed in K.S.A. 20-Feb-2017