

Arcrete SP145

High-Range Water Reducer with Set Retardation Effect for Hot Weather Concreting

ASTM C-494 Type F&G and BS EN 934-2

Description

Arcrete SP145 is a High-Range Water Reducer developed to enhance and improve the slump retaining properties of concrete, whilst providing improved ultimate compressive strengths also it improves the flow and strength development of concrete as it is highly flexible and effective over a wide range of cement contents and types.

Arcrete SP145 is especially beneficial in hot climate conditions.

Typical Properties

Appearance: Dark Brown Liquid

Specific Gravity: 1.180 at 20°C

Air Entrainment: 1% Max from Control Mix.

Chloride Content: Nil according to BS5075

Compatibility

With Cements:

Arcrete SP145 is compatible with all Portland, Pozzolanic and blast furnace cements. It is also compatible with concrete containing fly ash and silica fume.

With Other Admixtures:

Arcrete SP145 should not be premixed under any circumstances with other admixtures. The performance of the product will be affected by the presence of other chemical admixtures. We recommend Arkaz be contacted for Advice in these circumstances.

Addition Rates

Range:

0.5%-2.5% (v/w) by wt. of Total Binder.

The optimum dosage is assessed after preliminary trials depending upon the actual mix constituents and specifications required.

Addition rates outside of the recommended dosage range may be used for special concrete applications. In such circumstances it is important to conduct preliminary trials on the actual mix constituents to assess the effect on the properties of the concrete at the dosage level specified.

Effects of Overdosing

Serious overdosing of **Arcrete SP145** will generally produce a concrete mix of even greater workability, set retardation and a slight increase in air entrainment may be noticed. In SRC mixes and in cooler weather, set retardation will be further increased. If Intentional or accidental increased above the recommended addition rates are encountered, care must be taken to allow for the effect on the stripping time of formwork. In such cases, however, provided the concrete is properly cured the ultimate strength will generally be higher than for normal concrete.

Dispensing

It is preferable that **Arcrete SP145** should be introduced into the mixer by means of independent automatic dispensing equipment. Such equipment or advice on dispensing can be obtained from Arkaz.

Method of Use

Arcrete SP145 is supplied ready for use.

It should be added to concrete mixes either during the mixing cycle or at the same time as the water, or alternatively it should be added in its supplied form to a normal concrete mix a few minutes before the pour is made.

In the latter case further mixing should be provided to ensure complete dispersion.

Health and Safety

For further information, please consult Arkaz Technical Department

Technical Service

The technical service department of Arkaz Alsharq Building Materials is available to assist in the correct and best use of our products. These resources and advice are at your disposal entirely without obligation. Please contact:

Arkaz Alsharq Building Materials
Dammam 2nd Industrial Area - Road 135
PO Box 2572, Khobar, 31952
Saudi Arabia

Tel: 013 808 6970
Fax: 013 812 6541
info@arkaz.com
www.arkaz.com

The information given is based on data and knowledge considered to be true and accurate and is offered for the user's consideration, investigation and verification. Since the conditions of use are beyond our control we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale including those limiting warranties and remedies which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would violate or infringe statutory obligations or any rights belonging to a third party.

These products may be covered by patents or patents pending. Copyright 2015